



DEWALT Industrial Tools  
701 East Joppa Road  
Towson, MD 21286  
USA

Eurofins Product Testing A/S  
Smedeskovvej 38  
DK-8464 Galten  
Denmark

Tel. +45 70 22 42 76  
Fax +45 70 22 42 75  
voc@eurofins.dk  
www.eurofins.com/product-emissions

Date  
25 October 2016

Your ref.

Our ref.  
G15982E\_11

## Test Report – LEED 2009 EQ c4.1, SCAQMD rule 1168 (2005)

### Sample material

Sample identification	PE1000+
Product type	Construction Adhesive
Product data, according to manufacturer	Density: 1.41 g/ml at 23 °C ** Water content: 0 g/l** Exempt compounds***.
Date received	20 June 2012
Analytical period	July 2012

### Methods applied

Method	Principle	Parameter	Detection limit	Uncertainty
LEED 2009 EQ c4.1 ASTM D 2369 - 10	Gravimetric	Total Volatiles, SCAQMD rule 304	1 g/l	10 %

Volatile content of the sample was determined gravimetrically by heating up to 110 °C during 60 minutes. The result is the average of double testing. The result was calculated as:

$$([g \text{ all volatiles}] - [g \text{ water}] - [g \text{ exempt compounds}]) / ([l \text{ material}] - [l \text{ water}] - [l \text{ exempt compounds}])$$

U<sub>m</sub> (%): The expanded uncertainty U<sub>m</sub> is equal to 2 x RSD%, see also [www.eurofins.dk](http://www.eurofins.dk), keyword: Uncertainty.

### Analytical results

Solid content, % mass	Water content, % mass	Exempt compounds, % mass	VOC less water less exempt compounds, g/l	VOC limit g/l
97.4	0**	0***	37	70*

\* VOC limit for "Multipurpose Construction Adhesives"

\*\* Given by the client

\*\*\* No information about exempt compounds. Set to zero.

Eurofins Product Testing A/S

Maria Pelle  
Chemist